

## Technical Data sheet

### BETTERCOAT® 102

#### Alkyd Enamel 102

<b>Description</b>	Air-drying type long oil alkyd resin based.
<b>Use</b>	As the intermediate coat used between the alkyd resin based primer and enamel. Suitable for primed metallic and wooden surfaces
<b>Features</b>	<p>Easy application</p> <p>Provide excellent intecoat adhesion</p> <p>Provide smoother surface for overcoating.</p> <p>Tough film upon complete curing</p>
<b>Color</b>	<p>Glossy.</p> <p>White, other colors are available upon request</p>
<b>Technical data</b>	<p>Packing : 5kgs, 20kgs (Gross weight)</p> <p>Specific gravity: 1.1 -1.2 depending on color.</p> <p>Shelf life: 12 months.</p> <p>(Because of the environmental and the air, will be has skinning appearance during storage time)</p> <p>Flash point : 38°C</p>
<b>Application data</b>	<p>Application method: brush, roller or spray</p> <p>Thinner : Alkyd Thinner TP1100</p> <p>Thinning ratio : ready for use. If thinning is necessary, not more than 10% by weight.</p> <p>Spreading rate : 8~10m<sup>2</sup>/l/coat</p> <p>Dry film thickness : 35µm/coat</p> <p>Touch dry : 1 hour at 30°C</p> <p>Hard dry : 4 hours at 30°C</p> <p>Overcoating interval: Min 10 hours</p>
<b>Painting specification</b>	<p>Surface preparation: remove oil, grease and foreign matters before coating. If necessary, prepare by sanding to establish a smooth clean surface. If overcoating an existing coating,</p> <p>Primer: 01 coat of Betterprimer® 101</p> <p>Topcoat: 01~02 coats of Bettercoat® 102</p>
<b>Storage</b>	No excessive heat, sparks or flame.