

Technical Data sheet

BETTERCOAT® 202

Acrylic Enamel -Topcoat 202

Description	High build pigmented Acrylic vinyl resin based coating.
Use	For vehicle surface. Suitable for the prepared metallic surfaces such as trucks, tractors, industrial vehicles etc
Features	<p>Excellent adhesion.</p> <p>Outstanding weather resistance and color retention</p> <p>Fast drying, smooth and glossy .</p> <p>Colors are available upon request</p>
Technical data	<p>Packing : 5 kgs and 20 kgs.</p> <p>No. of components: Single</p> <p>Viscosity (28 °C) :Approx 70KU</p> <p>Pot life: (28 °C) : 4 hours</p> <p>Specific gravity: Approx 1.2</p> <p>Solid content : Approx 50%</p> <p>Flash point : 23°C</p>
Application data	<p>Application method: brush, roller, spray gun.</p> <p>Thinner : Acrylic Thinner 5~10%</p> <p>Shelf life : 12 months</p> <p>Spreading ratio : 9~10 m²/kg/coat</p> <p>Dry film thickness : 20~30 μm/coat</p> <p>Drying time :Surface dry : 10 minutes at 30 °C</p> <p>Hard dry : 8 hours at 30 °C</p> <p>Recoating interval :Min 8 hours .</p> <p>Max 14 months at 30 °C</p>
Painting specification	Surface preparation: For general usage such as tie coat, etc, ensures a clean, dry substrate.
Storage	Cool, dry, well, ventilated shade areas.
Safety precaution	<p>No excessive heat, sparks or flame.</p> <p>Use adequate ventilation. Avoid prolong contact with skin. Avoid breathing of vapor and spray mist. Use protective equipment. If the material comes in contact with the eye, immediately wash in running water for 20 minutes and obtain medical treatment. Observe all safe precautions.</p>