Better paint. An ISO 9001 Company

Technical Data sheet

BETTERFLOOR ® SL 700

Epoxy floor paint Solvent-free primer SL 700

Description A two packs polyamide cured epoxy resin based.

Use High performance floor coating in epoxy based protective coating system

where chemical and abrasion resistance is required on cement and

substrate surface, such as: warehouse, kitchen, electronics, manufacture...

Features Super corrosion resistance and adhesion.

Excellent chemical resistance, water and salt water resistant

Semi-transparent

Glossy

Technical Data Packing: 5 kgs/set và 20 kgs/set

No. of components: two

Viscosity (28 °C): approx 140KU

Mixing ratio: 100 (base) 50 (Hard) by weight

Pot life (28 °C): 30 mins Solid conent: 100%

Specific gravity: Approx. 1.10

Flash point: 35°C

Application data Application method : Roller

Thinner: useless
Shelf life: 12 months

Spreading rate: $4 \text{ m}^2/\text{kg/coat}$ Dry film thickness: $200 \,\mu\,\text{m/coat}$

Drying time: touch dry: 5 hours at 30°C

Hard dry: 24 hours at 30 °C

Recoating interval: Min 12 hours,

Max 14 months at ở 30 °C

Painting specification

coats.

Surface preparation: Ensure a clean dry for general usage, such as tie

Storage: cool, dry, well ventilated shaded areas.

Safety precaution No excessive heat, sparks or flame.

Use adequate ventilation. Avoid prolong contract with skin. Avoid breathing of vapor and spray mist. Use protective equipment. If the material comes in contract with the eye, immediately wash in running water for 20 minutes

and obtain medical treatment. Observe all safe precautions.

Test standard Compressive strength 80.00N/mm² ASTM C579

Tensile strength 25.00N/mm² ASTM C367
Water permeability Less than 1.0mm JIS K5400
Impact resistance 1/4′′ x 500g x 30 cm JIS K5400
Hardness 2H JIS K5400
Adhesion (Cross cut) 100/100 JIS K5400

Version 23-TDS 10-2023