Technical Data sheet

BETTERFLOOR ® WB 1000

Waterborne Epoxy Floor Paint -Topcoat WB 1000

| Description | A two packs waterborne curing agent with epoxy resin based. | | |
|------------------------|---|---|--|
| Use | High performance floor coating in epoxy based protective coating system where chemical and abrasion resistance is required on cement and substrate surface, such as: warehouse, kitchen, electronics, manufacture and hospital | | |
| Features | Super corrosion resistance and adhesion. Excellent chemical resistance Color : are available upon request. | | |
| Technical Data | Packing: 10 kgs/set và 20 kgs/set No. of components: two Viscosity (28 °C) : approx 90KU Mixing ratio: 1 (base) 1 (Hard) by weight Pot life (28 °C) : 40 minutes Solid content: 70% Specific gravity: Approx. 1.20 Flash point : 35 °C | | |
| Application data | Application method : brush, roller Thinner: ID water 5~10% Shelf life : 12 months Spreading rate : 4~5 m²/kg/coat Dry film thickness: 100 μ m/coat Drying time: touch dry : 3 hours at 30 °C Hard dry: 24 hours at 30 °C Recoating interval: Min 12 hours Max 12 months at ở 30 °C | | |
| Painting specification | Surface preparation: Ensure a clean dry for general usage, such as tie coats. Storage : cool, dry, well ventilated shaded areas . | | |
| Safety precaution | No excessive heat, sparks or flame. Use adequate ventilation. Avoid prolong contract with skin. Avoid breathing of vapor and spray mist. Use protective equipment. If the material comes in contract with the eye, immediately wash in running water for 20 minutes and obtain medical treatment. Observe all safe precautions. | | |
| Test standard | Compressive strength Tensile strength Water permeability Impact resistance Hardness Adhesion (Cross cut) | 80.00N/mm ² 35.00N/mm ² Less than 1.0mm 1/4´´ x 500g x 30 cm H 100/100 | ASTM C579 ASTM C367 JIS K5400 JIS K5400 JIS K5400 JIS K5400 |