

Technical Data sheet

BETTERPRIMER® 201

Acrylic Enamel -primer 201

Description	Acryl vinyl resin based primer incorporating rust inhibitive pigments .
Use	An excellent anti- rust and anti -corrosive for metal surface etc.
Features	<p>Excellent adhesion.</p> <p>Outstanding weather resistance.</p> <p>Fast drying.</p> <p>Colors : oxide red, platinum gray and matt black.</p>
Technical data	<p>Packing : 5 kgs and 20 kgs.</p> <p>No. of components: Single</p> <p>Viscosity (28 °C) :Approx 70KU</p> <p>Pot life: (28 °C) : 4 hours</p> <p>Specific gravity: Approx 1.3</p> <p>Solid content : Approx 50%</p> <p>Flash point : 35°C</p>
Application data	<p>Application method: brush, roller, spray gun.</p> <p>Thinner : Acrylic Thinner 10~30%</p> <p>Shelf life : 12 months</p> <p>Spreading ratio : 9~10 m²/kg/coat</p> <p>Dry film thickness : 20~30 μ m/coat</p> <p>Drying time :Surface dry : 10 minutes at 30 °C</p> <p>Hard dry : 8 hours at 30 °C</p> <p>Recoating interval :Min 8 hours .</p> <p>Max 14 months at 30 °C</p>
Painting specification	Surface preparation: For general usage such as tie coat, etc, ensures a clean, dry substrate.
Storage	Cool, dry, well, ventilated shade areas.
Safety precaution	<p>No excessive heat, sparks or flame.</p> <p>Use adequate ventilation. Avoid prolong contract with skin. Avoid breathing of vapor and spray mist. Use protective equipment. If the material comes in contract with the eye, immediately wash in running water for 20 minutes and obtain medical treatment. Observe all safe precautions.</p>